

ANION EXCHANGE RESIN TOKEM-841

TR 2227-016-72285630-2010

Strong base anion exchange resin (gel type) with uniform particle range composition. It possesses uniformity range of less than 1.1.

High monodispersity and the absence of small fraction contributes to significantly decreased pressure drop across the bed height. This, in turn, enables high flow rates enhancing regeneration effectiveness and reducing reagent and rinsing water requirements. Increased regeneration rate allows decreasing negative impact of organic substances on the anion exchange resin.

Uniform particle composition, compact bed packing, and no dead zones increase diffusion rate and contact area. These features lead to better ion exchange kinetics.

This monodispersed anion exchange resin is characterized with a high osmotic stability resulting in its longer service life compared to polydispersed products.

| GENERAL DESCRIPTION | |
|---------------------|--|
| Matrix | Styrene-DVB |
| Functional group | quaternary ammonium basic groups (type 1) |
| Polymer structure | gel |
| Ionic form | Cl ⁻ chloride OH ⁻ hydroxyl |

Application area:

Monodispersed anion exchange resin TOKEM-841 can be applied in all conventional water treatment systems, including:

- ionization water treatment systems with co-current regeneration;
- ionization water treatment systems with counter-current packed bed regeneration;
- as a bottom layer in the case layered charging of anion exchange resins in one filter.

Physical and Chemical Characteristics:

| CHARACTERISTICS | STANDARD VALUE |
|---|---|
| Appearance | Spherical transparent beads, white to brown in colour |
| Particle size range, mm | 0.60 ± 0.05 |
| Uniformity coefficient, max | 1.1 |
| Volume ratio of beads passing through N04 mesh, % max | 1.0 |

Table con' d (Physical and Chemical Characteristics)

| | |
|--|-----------|
| Volume ratio of beads on N08 mesh, % max | 2.0 |
| Moisture retention in Cl ⁻ form, % | 46-52 |
| Osmotic stability, %, min | 98 |
| Total uncracked beads as shipped, %, min | 95 |
| Total capacity in OH ⁻ form, mmol/cm ³ (mg-eq/cm ³), min | 1.0 |
| Equilibrium static exchange capacity in OH ⁻ form, mmol/cm ³ (mg-eq/cm ³), min | 0.9 |
| Oxidation of product in oxygen equivalent, mg/l, max | 0.55 |
| Shipping weight in Cl ⁻ form, g/cm ³ | 0.66-0.72 |
| Particle density, g/cm ³ | 1.06-1.10 |

Processing Characteristics:

| SUGGESTED OPERATING CONDITIONS AND MODES: | |
|--|------------|
| Bed depth min, mm | 800 |
| Pressure drop coefficient, kPa · h/m ² | 1.0 |
| Temperature limit, °C | |
| Cl ⁻ form | 80 |
| OH ⁻ form | 60 |
| pH limit | 0-14 |
| Swelling at Cl ⁻ → O H ⁻ , % | 30 |
| Regenerant, % | (3-4) NaOH |
| Total rinse requirement, BV | 2-4 |
| Backwashing bed expansion, % | 80-100 |